

PRODUCT DATA SHEET

Parex E70 Epoxy Grout

High strength epoxy resin-based grout

DESCRIPTION

Parex E70 Epoxy Grout is part of the Parex E Epoxy grout range cover a wide range applications and void thicknesses.

Parex E70 Epoxy Grout is a 4 component, high performance, precision, epoxy grouting system. Suitable for placing at temperatures between 5°C and 45°C.

USES

Parex E70 Epoxy Grout may only be used by experienced professionals.

- Machinery base plates.
- Crane rail tracks.
- Bridge Bearings.
- Compressors and pumps.
- Reciprocating machinery.
- High impact loads.

CHARACTERISTICS / ADVANTAGES

- High early strength and fast curing
- Also applicable at low temperatures (in conjunction with Parex E33 winter additive)
- Ready-to-mix, pre-batched units
- Non-shrink
- Corrosion and chemically resistant
- Stress and impact resistant
- High compressive strength
- Good creep resistance

PRODUCT INFORMATION

Composition	Epoxy resin
Packaging	Pre-batched unit 33.8kg (A + B + C + D)
Colour	Concrete grey
Shelf life	12 months
Storage conditions	Stored properly in original, unopened, sealed and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight.
Density	~2000 kg/m ³

TECHNICAL INFORMATION

Compressive strength	<u>1 day</u>	<u>63 N/mm²</u>	(EN 12190)
	<u>3 days</u>	<u>74 N/mm²</u>	
	<u>7 days</u>	<u>79 N/mm²</u>	
Typical grout values @ 20°C			
Modulus of elasticity in compression	~11.9 kN/mm ²		
Tensile strength in flexure	~22 N/mm ²		
Tensile strength	~10 N/mm ²		

APPLICATION INFORMATION

Yield	Each pack will yield approximately 16.75 litres of mixed material.
Layer thickness	Minimum grout depth: 35mm Maximum grout depth: 75mm
Flowability	Result from 50mm concentric ring test = 200mm Flow result of 50mm represents nil flow.
Ambient air temperature	+5°C min. / +45°C max.
Substrate temperature	+5°C min. / +45°C max.
Pot Life	~ 30 mins after mixing

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Minimum substrate temperature +5 °C
- The material must be conditioned by being stored in an area with an ambient temperature between +5 °C and +30 °C for a minimum of 48 hours before using.
- Do not thin with solvents. Solvents will prevent proper curing and change mechanical properties.
- Components C & D must be kept dry.
- For proper seating, allow the grout to rise above the bottom (3 mm) of the base plate.
- Avoid splitting pre-batched units to mix. Mix complete units only.
- Cold ambient, substrate or material temperatures will influence the curing and flow characteristics of Parex E70 Epoxy Grout.
- Do not subject cured epoxy grout to sudden temperature changes especially during early curing stages.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Mortar and concrete must be older than 28 days (dependent on minimum strength requirements). Verify the substrate strength (concrete, natural stone etc.).

The substrate surface (all types) must be clean, dry and free from contaminants such as dirt, oil, grease, existing surface treatments and coatings etc.

Steel substrates must be de-rusted to a standard equivalent to Sa 2.5.

The substrate must be sound and all loose particles must be removed.

Substrate must be dry or mat damp and free from any standing water, ice etc.

SUBSTRATE PREPARATION

Substrates must be sound, dry, clean and free from laitance, ice, standing water, grease, oils, old surface treatments or coatings and all loose or friable particles must be removed to achieve a laitance and contaminant free, open textured surface.

Surface and base plate contact area must be clean and sound. For best results, the substrate shall be dry. Remove dust, laitance, oils, grease, curing compounds, impregnations, waxes, foreign particles, coatings, and disintegrated materials by mechanical means, i.e. chipping with a chisel, blast cleaning etc.

All anchor pockets or sleeves must be free of water.

MIXING

Mixing of Parex E70 Epoxy Grout should be carried out with full packs only.

Pour all of the resin and hardener into a clean mixing vessel. Mix with a slow speed drill (200-300rpm) and Mortar Stirrer until homogeneous. Slowly add the filler to the mixed resin and hardener. When all the filler has been added, mix for a further two minutes until an even colour is achieved. Add the aggregate and mix for further minute until the aggregate is well dispersed throughout the mix. Try and ensure that air entrainment is kept to a minimum by keeping the mixing head below the surface level of the grout at all times. Larger volumes may be mixed using a forced action mixer such as the Creteangle or the Pennine.

APPLICATION METHOD / TOOLS

Allow mixed grout to stand for 5 minutes prior to placing to allow entrained air from mixing to be released. Place grout continuously into the work area from one side only. Where further mixes are required to fill the void, these should be prepared in sequence such that pouring is continuous. Place mixed grout within 30 minutes after start of mixing. Place in gap widths between 35mm and 75mm. For for voids outside of this use E20, E33 or E140 variants. Do not disturb the grouted section until the grout has hardened.

CLEANING OF EQUIPMENT

Sweep excess grout into appropriate containers for disposal before it has hardened.
Dispose of in accordance with applicable local regulations.
Uncured material can be removed with Sika Thinner C.
Cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

Parex E70 Epoxy Grout
March 2021, Version 01.01
020202010010000079

ParexE70EpoxyGrout-en-GBPAREX-(03-2021)-1-1.pdf