

PHENGUARD™ 940

DESCRIPTION

Two-component, high-build, amine adduct-cured novolac phenolic epoxy finish

PRINCIPAL CHARACTERISTICS

- Finish coat in the PHENGUARD tank coating system
- Excellent resistance to a wide range of organic acids, alcohols, edible oils, fats (regardless of free fatty acid content) and solvents
- Maximum cargo flexibility
- Low cargo absorption
- Good resistance to hot water
- Recognized corrosion control coating (Lloyd's register)
- Good application properties, resulting in a smooth surface
- Easy to clean

COLOR AND GLOSS LEVEL

- Light gray
- Eggshell

BASIC DATA AT 20°C (68°F)

| Data for mixed product | |
|---------------------------------------|--|
| Number of components | Two |
| Mass density | 1.7 kg/l (14.2 lb/US gal) |
| Volume solids | 66 ± 2% |
| VOC (Supplied) | Directive 1999/13/EC, SED: max. 191.0 g/kg max. 315.0 g/l (approx. 2.6 lb/US gal) |
| Recommended dry film thickness | 100 µm (4.0 mils) |
| Theoretical spreading rate | 6.6 m ² /l for 100 µm (265 ft ² /US gal for 4.0 mils) |
| Dry to touch | 2 hours |
| Overcoating Interval | Minimum: 24 hours Maximum: 21 days |
| Full cure after | See curing table |
| Shelf life | Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry |

Notes:

- See ADDITIONAL DATA - Spreading rate and film thickness
- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time



PHENGUARD™ 940

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Previous coat (PHENGUARD 935) must be dry and free from any contamination
- The substrate must be perfectly dry before and during application of PHENGUARD 940

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 10°C (50°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

SYSTEM SPECIFICATION

- PHENGUARD 930 (offwhite): 100µm (4.0 mils)
- PHENGUARD 935 (pink): 100µm (4.0 mils)
- PHENGUARD 940 (gray): 100µm (4.0 mils)

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 88:12

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance and slower cure
- Thinner should be added after mixing the components

Induction time

Allow induction time before use

| Mixed product induction time | |
|------------------------------|----------------|
| Mixed product temperature | Induction time |
| 15°C (59°F) | 20 minutes |
| 20°C (68°F) | 15 minutes |
| 25°C (77°F) | 10 minutes |

Pot life

4 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life



PHENGUARD™ 940

Air spray

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

2.0 mm (approx. 0.079 in)

Nozzle pressure

0.3 MPa (approx. 3 Bar; 44 p.s.i.)

Airless spray

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.46 – 0.53 mm (0.018 – 0.021 in)

Nozzle pressure

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 5%

Cleaning solvent

THINNER 90-53



PHENGUARD™ 940

ADDITIONAL DATA

| Spreading rate and film thickness | |
|-----------------------------------|---|
| DFT | Theoretical spreading rate |
| 100 µm (4.0 mils) | 6.6 m ² /l (265 ft ² /US gal) |
| 125 µm (5.0 mils) | 5.3 m ² /l (212 ft ² /US gal) |

Note: Maximum DFT when brushing: 60 µm (2.4 mils)

| Overcoating interval for DFT up to 100 µm (4.0 mils) | | | | | | |
|--|----------|-------------|-------------|-------------|-------------|--------------|
| Overcoating with... | Interval | 10°C (50°F) | 15°C (59°F) | 20°C (68°F) | 30°C (86°F) | 40°C (104°F) |
| itself | Minimum | 36 hours | 32 hours | 24 hours | 16 hours | 12 hours |
| | Maximum | 28 days | 25 days | 21 days | 14 days | 7 days |

Note: Surface should be dry and free from any contamination

| Curing time for DFT up to 100 µm (4.0 mils) | |
|---|--|
| Substrate temperature | Minimum curing time before transport of cargoes without note 4, 7, 8 or 11 and ballast water or tank test with sea water |
| 10°C (50°F) | 14 days |
| 15°C (59°F) | 14 days |
| 20°C (68°F) | 10 days |
| 30°C (86°F) | 7 days |
| 40°C (104°F) | 5 days |

Notes:

- Minimum curing time of PHENGUARD tankcoating system before transport of cargoes with note 4, 7, 8 or 11: 3 months
- For detailed information on resistance and resistance notes, please refer to the latest issue of the cargo resistance list
- For transport of methanol and vinyl acetate monomer, a hot cure is required, which cannot be substituted by a service period of 3-months with non-aggressive cargoes
- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- The performance of the applied system strongly depends on the curing degree of the first coat at time of recoating. Therefore overcoating time between 1st and 2nd coat is extended in comparison between 2nd and 3rd coat (see overcoating details)

| Pot life (at application viscosity) | |
|-------------------------------------|-----------|
| Mixed product temperature | Pot life |
| 10°C (50°F) | 6 hours |
| 20°C (68°F) | 4 hours |
| 30°C (86°F) | 1.5 hours |

PHENGUARD™ 940

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

| | | |
|--|-------------------|------|
| • CONVERSION TABLES | INFORMATION SHEET | 1410 |
| • EXPLANATION TO PRODUCT DATA SHEETS | INFORMATION SHEET | 1411 |
| • SAFETY INDICATIONS | INFORMATION SHEET | 1430 |
| • SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD | INFORMATION SHEET | 1431 |
| • SAFE WORKING IN CONFINED SPACES | INFORMATION SHEET | 1433 |
| • DIRECTIVES FOR VENTILATION PRACTICE | INFORMATION SHEET | 1434 |
| • CLEANING OF STEEL AND REMOVAL OF RUST | INFORMATION SHEET | 1490 |
| • SPECIFICATION FOR MINERAL ABRASIVES | INFORMATION SHEET | 1491 |
| • RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE | INFORMATION SHEET | 1650 |

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

